

LEGACY ULTRA FLAT

TDS01-220

| | |
|----------------------------|--|
| DESCRIPTION | A high opacity acrylic flat finish for ceilings. Versatile application properties allow roller or spray application with exceptional results. |
| TYPICAL USES | General interior ceilings (Dry areas). |
| PERFORMANCE | Excellent coverage with very flat and even finish. Negligible side sheen. Excellent masking of surface imperfections from reflected light. Excellent adhesion. |
| LIMITATIONS | Do not apply if the air and surface temperature during application and drying is likely to fall below 10°C. Not recommended for wet areas. |
| TECHNICAL DATA | Resin: Acrylic Co-polymer Product Type: Flat Acrylic Solvent: Water Appearance: White Colour: All Colours Primer: See over. Durability: Excellent Thinning and Clean Up: Water Pack Size: 4, 10 Litre VOC: <40g/litre Vol Solids: 38 percent Touch Dry: 60 minutes @20°C Recoat Time: 2 Hours @20°C Number of Coats: 2 Theoretical Coverage: 12 m ² /litre/coat Wet Film Thickness: 100 microns Dry Film Thickness: 38 microns |
| SPREAD RATE | 10-12 - m ² /litre/coat Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness. |
| PRODUCT CODES | 01-220.04 01-220.10 01-2205.10 |
| SURFACE PREPARATION | <p>Plasterboard-Previously Painted Good Treat and kill any areas of mould or fungal infestation. When fully killed clean the surface with Liquid sugar soap then rinse off any residual cleaner with clean water to remove all residual chemicals. Allow to dry.</p> <p>Thoroughly scrape and sand to remove all loose and flaking paint. Sand remaining flaking paint to a feathered edge, taking care not to fur up the underlying plasterboard surface. Spot prime any bare substrate.</p> <p>Fill all cracks or holes with TRUEPREP STOP-IT FILLER, or suitable stopping compound for larger repairs. Once dry sand smooth. Pole sand P240 all remaining surfaces and dust down.</p> <p>Seal all repaired areas and any areas of bare substrate with the manufactures recommended sealer/ undercoat.</p> <p>If there are any signs of water-staining that is visible on the walls or ceilings. We would recommend to seal that entire surface with TRUEPREP MULTIPURPOSE ALKYD PRIMER UNDERCOAT or TRUEPREP MULTIPRIME. Contact to Cotec Technical if in doubt.</p> |
| APPLICATION | <p>For most surfaces apply 1 or 2 coats of TRUEPREP EASYSAND or DRYWALL SEALER primer, in accordance with its data sheet. For premium finish 2 coats of TRUEPREP EASYSAND or 1 coat of DRYWALL SEALER applied at 6-8sqM/l, will result in a better-quality finish overall. Round head pole sand to an acceptable uniform surface, with #180-220 grit sandpaper.</p> <p>Brush or roller: A Wooster Pro-Dooz sleeve (with a 10 mm nap) roller is preferred. Stir paint well before use. Recommend two coats to achieve maximum coverage. Allow 2 hours between coats.</p> <p>Spray: 513-515 Tip.</p> |

THINNING Do not thin. Clean up in water. Use a small amount of detergent to aid clean up.

ENVIRONMENTAL This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET

COATING TECHNOLOGIES LIMITED

10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.